

We Claim:

1. (Amended) A method of manufacturing a metallic current collector for use in an electrochemical [of] or galvanic cell, comprising the steps of:

5

(i) perforating a solid, flat metal strip using a continuous process that results in deformation of the strip at least locally near the perforations; and

10

(ii) Immediately following step (i), annealing the perforated strip at a temperature below the melting point of said metal or metal-alloy to yield a recrystallized microstructure therein.

15

2. A method according to claim 1, wherein said recrystallized microstructure contains a minimum of 50% special grain boundaries.

3. A method according to claim 1, wherein said continuous process is a process of reciprocating expansion.

20

4. A method according to claim 1, wherein said continuous process is a process of rotary expansion.

5. A method according to claim 1, wherein said continuous process comprises punching perforations through said metal strip.

25

6. A method according to claim 1, wherein said metal is selected from lead or a lead alloy.

7. A method according to claim 2, wherein said metal is selected from lead or a lead alloy.